

Bear Brand TUFNOL

Cotton fabric based laminate

Medium weave cotton/phenolic resin laminated plastic

(SRBF - Synthetic Resin Bonded Fabric)

For lubricated bearings.

Bear Brand TUFNOL is a cotton fabric grade specially formulated for use as a lubricated bearing material. It has enhanced wearing properties and dimensional stability and gives excellent performance in a multitude of bearing applications, using water as a lubricant, or more conventional oils or greases. The low water absorption properties allow reduced clearances in bearings and also provide enhanced electrical insulation properties.

What is Bear Brand used for?

Bear Brand is used for a wide range of wearing and bearing applications, such as oil or grease lubricated bearings, slideways, water lubricated marine bearings, pump sleeve bearings, seal rings, mixer bearings, slipper pads, rolling mill bearings, guide bushes and a wide variety of components which are lubricated by the water-based process fluids in which they operate.

TYPES AVAILABLE	Sheets	Rods	Tubes	Other sections
Natural colour	Yes	Yes	Yes	Yes
Graphite-impregnated Bear Brand	Yes*	Yes*	Yes*	Yes*
Molybdenum disulphide impregnated	Yes*	No	No	No
Bear Brand				





SPECIFICATIONS for Bear Brand TUFNOL

BRITISH STANDARDS Current Standards Recent Standards (now

obsolete)

Sheet Since the withdrawal of BS 2572, no BS 2572 Type F2/1

British Standards or other national standards are applicable to Bear Brand Tufnol. This grade is therefore now manufactured to in-house quality specifications of Tufnol Composites Ltd, based on the former BS 2572

Type F2/1.

Round Rod BS EN 61212-3-3 Type PF CC 42 BS 6128 Part 2 Type PF CC 23

Rectangular Bar BS 6128 Part 4 Type PF CC 44

Hexagon Bar BS 6128 Part 6 Type PF CC 64

Round Tube BS EN 61212-3-2 Type PF CC 32 BS 6128 Part 9 Type PF CC 93

Rectangular Tube BS 6128 Part 13 Type PF CC 133





PHYSICAL PROPERTIES

Bear Brand TUFNOL Sheet

PROPERTY	TYPICAL RESULT	UNITS
Cross breaking strength	110	MPa
Impact strength, notched, Charpy	11.0	kJ/m2
Compressive strength, flatwise	290	MPa
Compressive strength, edgewise	210	MPa
Shear strength, flatwise	100	MPa
Tensile strength	58	MPa
Young's modulus	6.6	GPa
Water Absorption		
- 3mm thk.	45	mg
- 6mm thk.	80	mg
- 12mm thk.	100	mg
Electric strength, flatwise in oil at 90°C		
- 3mm thk.	3.9	MV/m
- 6mm thk.	3.5	MV/m
Electric strength, edgewise in oil at 90°C	15	kV
Insulation resistance after immersion i water	in5x1010	ohms
Relative density	1.32	-





Maximum working temperature**

- continuous	120	°C
- intermittent	130	°C
Thermal classification	Class E	-
Thermal conductivity through laminae	0.29	W/(mK)
Thermal expansion in plane of laminae	2.7	X 10-5/ K
Specific heat	1.5	kJ/(kgK)

Test methods as BS EN 60893-2, where applicable.

Bear Brand TUFNOL Round Tube

PROPERTY	TYPICAL RESULT	UNITS
Axial compressive strength	170	MPa
Cohesion between layers	110	MPa
Water absorption	2.0	mg/cm2
Insulation resistance after immersion water	in1x108	ohms
Relative density	1.32	-

Test methods as BS EN 61212-2, where applicable.





Bear Brand TUFNOL Round Rod

PROPERTY	TYPICAL RESULT	UNITS
Flexural strength	110	MPa
Water absorption	2.0	mg/cm2
Insulation resistance after immersion water	in5x107	ohms
Axial electric strength in oil at 90°C	6	kV
Relative density	1.32	-

Test methods as BS EN 61212-2, where applicable.



^{**}Users of highly stressed components at temperatures approaching the maximum are recommended to seek further advice from Tufnol Composites Ltd.